

Alloy 36 ist eine Nickel-Eisen-Legierung mit geringer Wärmeausdehnung, Nickelanteil 36%. Sie ist im Normalbereich atmosphärischer Temperaturen fast masskonstant und besitzt einen niedrigen Ausdehnungsbeiwert von tiefkalten Temperaturen bis ca. + 260°C. Die Legierung behält im Tieftemperaturbereich ausserdem ihre gute Festigkeit und Zähigkeit. Verwendung für Längennormale, Messgeräte, Laserbauteile, Bimetall-Thermostatband, Thermostatstäbe sowie für Behälter und Rohrleitungen zum Transport von Flüssiggas.

A nickel-iron low-expansion alloy containing 36% nickel. It maintains nearly constant dimensions over the range of normal atmospheric temperatures, and has a low coefficient of expansion from cryogenic temperatures to about 500°F (+ 260°C). The alloy also retains good strength and toughness at cryogenic temperatures. Used for standards of length, measuring devices, laser components, bimetal thermostat strip, thermostat rods, and tanks and piping for storing and transporting liquefied gases.

|   |  |   |
|---|--|---|
| Produktformen<br>Product forms  | Blech, Rundstab, Rohr, Draht, Schmiedematerial   | Sheet, Plate, Round Bar, Pipe, Tube, Wire, Forging Stock  |
| Normen und<br>Bezeichnungen<br>Major<br>Specifications  | UNS K93600<br>ASTM F 30<br>DIN 385, 1715<br>W-Nr.: 1.3912  | UNS K93600<br>ASTM F 30<br>DIN 385, 1715<br>W-Nr.: 1.3912   |
| Physikalische<br>und Thermische<br>Eigenschaften<br><br>Physical and<br>Thermal<br>Properties | Dichte, lb/in <sup>3</sup><br>g/cm <sup>3</sup><br>Schmelztemperatur (etwa)<br>°F<br>°C<br>Wendepunkt, °F<br>°C<br>Wärmeleitfähigkeit, Btu • in/ft <sup>2</sup> •h•°F<br>W/m•°C<br>Ausdehnungsbeiwert,<br>68 - 212°F, 10-6 in/in•°F<br>68 - 392°F, 10-6 in/in•°F<br>20 - 100°C, µm/m•°C<br>20 - 200°C, µm/m•°C<br>Spez. elektr. Widerstand,<br>ohm•circ mil/ft<br>ohmm•m<br>71<br>490<br>35<br>240<br>42 | Density, lb/in <sup>3</sup><br>g/cm <sup>3</sup> .<br>Melting Temperature (approximate),<br>°F<br>°C<br>Inflection Point, °F<br>°C<br>Thermal Conductivity, Btu • in/ft <sup>2</sup> •h•°F<br>W/m•°C<br>Coefficient of Expansion,<br>68 - 212°F, 10-6 in/in•°F<br>68 - 392°F, 10-6 in/in•°F<br>20 - 100°C, µm/m•°C<br>20 - 200°C, µm/m•°C<br>Electrical Resistivity,<br>ohm•circ mil/ft<br>ohmm•m<br>0.293<br>8.11<br>2610<br>1430<br>430<br>220<br>69.3<br>10.0<br>0.83<br>1.4<br>1.5<br>2.6<br>480<br>0.800<br>0.293<br>8.11<br>2610<br>1430<br>430<br>220<br>69.3<br>10.0<br>0.83<br>1.4<br>1.5<br>2.6<br>480<br>0.800 |
| Mechanische<br>Eigenschaften<br><br>Mechanical<br>properties                                  | (Geglüht)<br>Zugfestigkeit, ksi<br>MPa<br>Streckgrenze (0.2% Dehngrenze),<br>ksi<br>MPa<br>Dehnung, %<br>71<br>490<br>35<br>240<br>42  | (Annealed)<br>Tensile Strength, ksi<br>MPa<br>Yield Strength (0.2% Offset),<br>ksi<br>MPa.<br>Elongation, %<br>71<br>490<br>35<br>240<br>42   |

Die Richtigkeit kann nicht garantiert werden.

The correctness cannot be guaranteed.